



Nitoflor® DS2000

2-3mm self smoothing epoxy decorative floor topping

Uses

Nitoflor DS2000 provides a hard-wearing decorative floor which is chemical resistant, impervious and extremely easy to clean.

Nitoflor DS2000 is ideal for industrial or commercial locations where a hard-wearing, hygienic, dust-free environment is important (e.g. laboratories, hospital clean rooms, electronics assembly plants, switchgear plant rooms, pharmaceutical industries, food processing industries, showrooms, light industrial plants).

Advantages

- **Hygienic** - Self smoothing formulation provides a dust-free, seamless floor which is extremely easy to clean
- **Easy to lay** - Excellent rate of application can be achieved.
- **Hard-wearing** - Good abrasion resistance. Withstands foot and vehicular traffic.
- **Chemical resistant** - Very good resistance to many industrial chemicals

Description

Nitoflor DS2000 is a special blend of selected epoxy resins, curing agents and graded inert coloured aggregates which, when mixed, provides a 2 - 3mm epoxy resin floor topping with unique laying properties. The materials are supplied in preweighed packs ready to mix and use on site. The system includes a two part epoxy resin primer, Nitoprime 25, which is also supplied in ready to use pre-weighed packs.

Technical Support

Fosroc offers a technical support service to specifiers, end users and contractors, as well as on-site technical assistance in locations all over the country.

Properties

Material Properties

Nitoprime 25	20°C	35°C
Pot life	90 min.	30 min.
Max. overlay time with Nitoflor DS2000	24 hrs.	18 hrs.

Nitoflor DS2000

Pot life	60 min.	30 min.
-----------------	---------	---------

Initial cure

Light foot traffic	24 hours	18 hours
Full cure (Vehicular traffic)	7 days	5 days

Physical properties

Nitoflor DS2000

Specific Gravity	1.70
-------------------------	------

Compressive strength (to BS 6319, pt 2)	80 N/mm ²
--	----------------------

Flexural strength (to BS 6319, pt 3)	40 N/mm ²
---	----------------------

Tensile strength (to BS 6319, pt 7)	20 N/mm ²
--	----------------------

Bond strength to primed concrete substrate (Elcometer tensile pull off)	Greater than cohesive strength of concrete
--	--

Abrasion resistance (ASTM D 4060)	0.1mg /cycle - loss of weight(with CS17 wheel of 1000g weight)
--	---

Shore D Hardness as per ASTM D 2240	80
--	----

Chemical resistance

Nitoflor DS2000 is resistant to a wide range of chemicals. Specific data is available on request.

Specification clauses

Self smoothing epoxy floor topping applied on epoxy primed concrete surface within 18 hours at 35°C. When tested as per BS6319, Nitoflor DS2000 shall possess a minimum compressive strength of 50N/mm², a flexural strength of 34N/mm², and a minimum tensile strength of 16 N/mm², and offer an minimum abrasion resistance of 0.1mg/cycle when tested as per ASTM D4060, with CS17 wheel of 1000g weight. It must also have a hardness of 80, when tested for Shore D Hardness.

Nitoflor® DS2000

Application instructions

Self-smoothing is a term used in the flooring industry to describe a composition which after being spread to a uniform layer of appropriate thickness, develops a smooth, resin-rich surface without the need for skilful trowelling. This self-smoothing action is very localised and does not eradicate irregularities of level present in the original substrate. It is most important, therefore, that adequate surface preparation and repair is undertaken prior to application of Nitoflor SL flooring systems. Advice on specific applications may be obtained from Fosroc.

All floors to receive Nitoflor DS2000 floor topping should be protected by means of a damp-proof membrane. The absence of such membranes could lead to the problem of osmosis/rising dampness where soluble salts have concentrated.

New concrete or cementitious substrates should have been placed at least 28 days earlier and have a moisture content of less than 5% before topping with Nitoflor DS2000 floor topping. This can be checked by using a Thermo Hygrometer.

Surface preparation

The long term durability of the applied Nitoflor DS2000 topping is dependent upon the adhesive bond achieved between the flooring material and substrate. It is most important therefore, that substrate surfaces are correctly prepared prior to application.

All substrates should be sound and free from contamination such as mortar and paint splashes, curing compound residue, oil or grease. Excessive laitence should be removed by light mechanical scabbling, grinding or grit blasting. Light laitence may be removed by acid etching with Reebaklens followed by thorough washing with clean water, vacuum cleaning and then allowing the surface to dry.

Oil and grease contamination must be completely removed by grinding down to sound, clean concrete. Alternatively, blasting techniques can be used to provide the required substrate.

Old concrete floors with deep seated contamination and substrate damage must be prepared by any of the mechanical methods as previously described. Major discrepancies in the substrate should be repaired with Nitomortar S.

Where these methods are considered impracticable, alternative methods may be considered, but it is essential that a sound, clean substrate be provided. For further advice, Fosroc may be consulted.

As Nitoflor DS2000 is only a 1.5 - 3mm topping, the substrate must be relatively even textured, as any major surface discrepancies may show through, or may cause colour variation in the applied topping.

Priming

Prepared substrates to be treated with Nitoflor DS2000, should be primed with Nitoprime 25.

Nitoprime 25 should be mixed in the proportions supplied by adding the entire contents of hardener to the base. Once mixed the Nitoprime 25 should be immediately applied in a thin, continuous film using stiff brushes or rollers. Over application and puddles should be avoided.

Porous floors may require two coats of Nitoprime 25.

Nitoprime 25 should be allowed to become tack free prior to application of Nitoflor DS2000. (Reference maximum overcoat time, product properties).

Mixing

Nitoflor DS2000 is supplied in pre-weighed packs ready to use on site. Solvent or thinners, should not be added. A forced action mixer with a paddle fitted into a heavy duty, slow speed electric hand drill is recommended for mixing.

Hardener component is mixed with Base resin in a suitable mixing vessel. The full colour paste is then added and mixed until an even colour is obtained. Finally the filler as supplied is added and mixed further for three minutes until a homogenous lump free slurry is obtained.

Where bulk mixing is required, Fosroc must be consulted.

Serrated steel trowel designed to lay 2mm Nitoflor DS2000.

Laying

The material is poured onto the primed substrate and spread to the required thickness with a steel trowel. Alternatively, a serrated trowel can be used. The resin floor should not be overworked but spread slowly and evenly.

Nitoflor® DS2000

Immediately after spreading, the floor should be firmly rolled with a spiked roller to help release any entrapped air in the material and level any slight trowel marks. The floor should now self-smooth to an even coloured dense, impervious floor.

Note

- In certain conditions, a light oily film may appear on the surface of the floor on curing. This may be easily removed after a minimum curing period of 48 hrs, by washing with a liquid detergent floor cleaner and water.
- For application on steel substrates, consult Fosroc.

Expansion joints

Nitoflor DS2000 floor topping should be discontinuous over sealants in joints unless otherwise specified.

Cleaning

Tools and equipment should be cleaned with Nitoflor Sol immediately after use. Spillages should be absorbed with sand or sawdust and disposed in accordance with local regulations.

Limitations

Nitoflor DS2000 is available in limited decorative surface finishes. For special colour combination, contact Fosroc Technical Services.

It is not compatible for application over asphalt, unmodified sand-cement screeds or PVC tiles and sheets. Nitoflor DS2000 laid floor will be scratched due to nails or sharp objects protruding from machinery, packings, or trolleys moving on the floor. Presence of sand will also cause abrasion.

The product is not advised to be applied below 15°C as the flow reduces. While applying the product above 35°C, there can be a problem of low pot life etc., and it will be difficult to apply the material. Cured product is not suitable for exposure to subzero temperatures and above 65°C.

When there is not enough material in a given area, roller marks caused due to spiked rolling may not close which will result in an undesirable finish.

The product is not suitable for areas exposed to direct sunlight.

Estimating

Packing and coverage

	Pack size	Coverage
Nitoprime 25	1 & 4 L	Typically 4 - 6 m ² per kg
Nitoflor DS2000	17kg	Typically at 3mm thickness, 3.3 m ² per pack, depending on the substrate.

Primer coverage will depend on the texture and porosity of the substrate and also the application thickness.

Storage

In unopened packs, Nitoflor DS2000 and Nitoprime 25 have a shelf life of 12 months when stored in warehouse conditions below 35°C.

Precautions

Health and Safety instructions

Nitoflor DS2000 base and hardener components, colour paste, Nitoprime 25 and Nitoflor Sol should not come in contact with skin and eyes or be swallowed. Prolonged inhalation of solvent vapours should be avoided.

Since some people are sensitive to epoxy resins, hardeners and solvents, gloves, goggles and barrier creams should be used. Adequate ventilation should be avoided and if work is in enclosed areas, suitable breathing apparatus must be used.

If mixed resin comes in contact with skin, it must be removed before it hardens with a resin removing cream, followed by washing with soap and water. Solvent should not be used. Contamination of skin with any of the above component products should be removed immediately with soap and water.

Should accidental eye contamination occur with any of the above products, it should be washed well with plenty of clean water and medical advice sought. If swallowed, immediate medical attention is advised.



Nitoflor® DS2000

Fire

Nitoflor DS2000 hardener, Nitoprime 25 and Nitoflor Sol are flammable and should not be exposed to naked flames or other sources of ignition. Smoking is prohibited. Containers should be tightly sealed when not in use. Fire should be extinguished with Carbon dioxide or foam. Vomiting should not be induced.

Flash points

Nitoflor DS2000 Hardener	39°C
Nitoprime 25	25°C
Nitoflor Sol	33°C

Additional information

The Nitoflor range of industrial flooring products for most industrial environments such as abrasion, chemical attack and impact. The product range includes coatings, toppings and sealants to meet the requirements of end users such as workshops, food and drink manufacturing industries, warehouses, hospitals, laboratories, steel, sugar and paper industries, aircrafts, hampers, mechanical engineering industries, tanneries, refineries, etc. For specific requirements, contact Fosroc.

Separate datasheets are available on these products.

® Denotes the trademark of Fosroc International Limited

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone	fax	e-mail
++91 80-22240018/120	++91 80-22233474	india@fosroc.com

Regional Offices



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

111/3, Hafeeza Chamber II Floor,
K H Road, PBNo. 2744, Bangalore 560027
www.fosroc.com

Bangalore

Shankar House, IV Floor
1 & 18, RMV Extension
Bangalore 560 080
Ph:080-2361 3161/2361 2004
Fax : 080-2361 7454
email: Bangalore@fosroc.com

Mumbai

208/209, Persepolis
Sector 17, Vashi
Navi Mumbai 400 703
Ph:022-2789 6412/14
Fax: 022 - 2789 6413
email:Mumbai@fosroc.com

Delhi

First floor,1/2 East Patel Nagar
Opp: Vivek Cinema, Main Patel Rd
New Delhi 110 008
Ph:011-25884903/4
Fax: 011- 25884422
email:Delhi@fosroc.com

Kolkata

P-569, Lake Terrace Extn.
First Floor
Kolkata 700 029
Ph: 033 24650917 / 55343188
Fax: 033-24650891
email:Kolkata@fosroc.com

- Ahmedabad : (079) 26762799 ● Ankleshwar : (02646) 220704/224687 ● Bhubaneshwar : (0674) 2546415 ● Chennai (044) 24899949/24853383
- Chandigarh : (0172) 2639360 ● Cochin : (0484) 2356668 ● Coimbatore : (0422) 2472966 ● Goa : (0832) 2542465 ● Guwahati (0361) 2548793
- Hyderabad : (040) 27662324/27662425 ● Hubli (0836) 09343402597 ● Indore : (0731) 504339/5061477 ● Jaipur : (0141) 2235349
- Jamshedpur: (0657) 2223848 ● Lucknow : (0522) 2239044 ● Nagercoil 09842134873 ● Visakhapatnam : (0891) 2564850 / 2707607