



# Nitoflor® EPU2000

## 2 mm self-smoothing epoxy polyurethane floor topping

### Uses

Nitoflor EPU2000 provides a hard-wearing attractive floor which is chemical resistant, impervious and extremely easy to clean.

Available in a wide range of colours, Nitoflor EPU2000 is ideal for industrial or commercial locations where a hard-wearing, hygienic, dust-free environment is important (e.g. laboratories, hospital clean rooms, electronics assembly plants, switchgear plant rooms, pharmaceutical industries, food processing industries, showrooms, light industrial plants).

### Advantages

- **Hygienic** Self smoothing formulation provides a dust-free, seamless floor which is extremely easy to clean
- **Easy to lay** Excellent rate of application can be achieved.
- **Hard-wearing** Good abrasion resistance. Withstands foot and vehicular traffic.
- **Chemical resistant** Very good resistance to many industrial chemicals
- **Attractive** Available in a wide range of colours to provide a very attractive floor finish.

### Description

Nitoflor EPU2000 epoxy polyurethane coating is a special blend of selected epoxy resins, curing agents and graded inert aggregates which, when mixed, provides a 2 mm epoxy resin floor topping with unique laying properties. The materials are supplied in preweighed packs ready to mix and use on site. The system includes a two part epoxy resin primer, Nitoprime 25, which is also supplied in ready to use pre-weighed packs.

### Technical Support

Fosroc offers a technical support service to specifiers, end users and contractors, as well as on-site technical assistance in locations all over the country.

### Properties

#### Material Properties

Nitoprime 25	20°C	35°C
Pot life	90 min.	30 min.

#### Max. overlay time with Nitoflor EPU2000 epoxy polyurethane coating

	24 hours	18 hours
--	----------	----------

#### Nitoflor EPU2000 epoxy polyurethane floor topping

Pot life	60 min.	30 min.
----------	---------	---------

Initial cure (light foot traffic)	24 hours	18 hours
-----------------------------------	----------	----------

Full cure (Vehicular traffic)	7 days	5 days
-------------------------------	--------	--------

#### Physical properties

##### Nitoflor EPU2000

Compressive strength (to BS 6319, pt 2)	56 N/mm <sup>2</sup>
---	----------------------

Flexural strength (to BS 6319, pt 3)	33 N/mm <sup>2</sup>
--------------------------------------	----------------------

Tensile strength (to BS 6319, pt 7)	14 N/mm <sup>2</sup>
-------------------------------------	----------------------

Bond strength to primed	Greater than cohesive concrete substrate strength of concrete (Elcometer tensile pull off)
-------------------------	--

Abrasion resistance (ASTM D 4060)	0.1mg /cycle - loss of weight( with CS17wheel of 1000g weight)
-----------------------------------	--

Shore D Hardness as per ASTM D 2240	80
-------------------------------------	----

#### Chemical resistance

Nitoflor EPU2000 epoxy polyurethane coating is resistant to a wide range of chemicals. Specific data is available on request.

# Nitoflor® EPU2000

---

## Specification clauses

Self smoothing flow applied epoxy polyurethane coating applied on epoxy primed concrete surface within 18 hours at 35°C. When tested as per BS 6319, Nitoflor EPU2000 epoxy polyurethane coating shall possess a minimum compressive strength of 50N/mm<sup>2</sup>, a flexural strength of 34N/mm<sup>2</sup>, and a minimum tensile strength of 16N/mm<sup>2</sup>, and offer an minimum abrasion resistance of 0.1mg/cycle when tested as per ASTM D4060, with CS17 wheel of 1000gms weight. It must also have a hardness of 80, when tested for Shore D Hardness.

## Application instructions

Self-smoothing is a term used in the flooring industry to describe a composition which after being spread to a uniform layer of appropriate thickness, develops a smooth, resin-rich surface without the need for skilful trowelling. This self-smoothing action is very localised and does not eradicate irregularities of level present in the original substrate. It is most important, therefore, that adequate surface preparation and repair is undertaken prior to application of Nitoflor SL flooring systems. Advice on specific applications may be obtained from Fosroc.

All floors to receive Nitoflor EPU2000 epoxy polyurethane coating should be protected by means of a damp-proof membrane. The absence of such membranes could lead to the problem of osmosis/rising dampness where soluble salts have concentrated.

New concrete or cementitious substrates should have been placed at least 28 days earlier and have a moisture content of less than 5% before topping with Nitoflor EPU2000 epoxy polyurethane coating. This can be checked by using a Thermo Hygrometer.

### Surface preparation

The long term durability of the applied Nitoflor EPU2000 epoxy polyurethane coating is dependent upon the adhesive bond achieved between the flooring material and substrate. It is most important therefore, that substrate surfaces are correctly prepared prior to application.

All substrates should be sound and free from contamination such as mortar and paint splashes, curing compound residue, oil or grease. Excessive laitence should be removed by light mechanical scabbling, grinding or grit blasting. Light laitence may be removed by acid etching with Reebaklens followed by thorough washing with clean water, vacuum cleaning and then allowing the surface to dry.

Oil and grease contamination must be completely removed by grinding down to sound, clean concrete. Alternatively, blasting techniques can be used to provide the required substrate.

Old concrete floors with deep seated contamination and substrate damage must be prepared by any of the mechanical methods as previously described. Major discrepancies in the substrate should be repaired with Nitomortar S.

Where these methods are considered impracticable, alternative methods may be considered, but it is essential that a sound, clean substrate be provided. For further advice, Fosroc may be consulted.

As Nitoflor EPU2000 epoxy polyurethane coating is only a **2mm** topping, the substrate must be relatively even textured, as any major surface discrepancies may show through, or may cause colour variation in the applied topping.

### Priming

Prepared substrates to be treated with Nitoflor EPU2000 epoxy polyurethane coating, should be primed with Nitoprime 25 primer

Nitoprime 25 primer should be mixed in the proportions supplied by adding the entire contents of hardener can to the base can. Once mixed the Nitoprime 25 should be immediately applied in a thin, continuous film using stiff brushes or rollers. Over application and puddles should be avoided.

Porous floors may require two coats of Nitoprime 25 primer. Nitoprime 25 primer should be allowed to become tack free prior to application of Nitoflor EPU2000 epoxy polyurethane coating. (Reference maximum overcoat time, product properties ).



# Nitoflor® EPU2000

## Mixing

Nitoflor EPU2000 epoxy polyurethane coating is supplied in pre-weighed packs ready to use on site. Solvent or thinners, should not be added. A forced action mixer with a paddle fitted into a heavy duty, slow speed electric hand drill is recommended for mixing.

Hardener component is mixed with Base resin in a suitable mixing vessel. The full colour paste is then added and mixed until an even colour is obtained. Finally the filler as supplied is added and mixed further for three minutes until a homogenous lump free slurry is obtained.

Where bulk mixing is required, Fosroc must be consulted.

## Laying

The material is poured onto the primed substrate and spread to the required thickness with a steel trowel. Alternatively, a serrated trowel can be used. The resin floor should not be overworked but spread slowly and evenly.

Immediately after spreading, the floor should be firmly rolled with a spiked roller to help release any entrapped air in the material and level any slight trowel marks. The floor should now self-smooth to an even coloured dense, impervious floor.

## Note

- In certain conditions, a light oily film may appear on the surface of the floor on curing. This may be easily removed after a minimum curing period of 48 hrs, by washing with a liquid detergent floor cleaner and water.
- For application on steel substrates, consult Fosroc.

## Expansion joints

Nitoflor EPU2000 epoxy polyurethane coating should be discontinuous over sealants in joints unless otherwise specified.

## Cleaning

Tools and equipment should be cleaned with Nitoflor Sol solvent immediately after use. Spillages should be absorbed with sand or sawdust and disposed in accordance with local regulations.

## Limitations

It is not compatible for application over asphalt, unmodified sand-cement screeds or PVC tiles and sheets. Nitoflor EPU2000 epoxy polyurethane coating laid floor will be scratched due to nails or sharp objects protruding from machinery, packings, or trolleys moving on the floor. Presence of sand will also cause abrasion.

The product is not advised to be applied below 15°C as the flow reduces. While applying the product above 35°C, there can be a problem of low pot life etc., and it will be difficult to apply the material. Cured product is not suitable for exposure to subzero temperatures and above 65°C.

When there is not enough material in a given area, roller marks caused due to spiked rolling may not close which will result in an undesirable finish.

The product is not suitable for areas exposed to direct sunlight.

## Estimating

### Packing and coverage

	Pack size	Coverage
<b>Nitoprime 25</b>	1 L / 4 L	5.5-6.5 m <sup>2</sup> /L
Primer coverage will depend on the texture and porosity of the substrate and also the application thickness.		
<b>Nitoflor EPU2000</b>	15L	Typically at 2mm thickness, 5 m <sup>2</sup> /L depending on the substrate.



# Nitoflor® EPU2000

## Storage

In unopened packs, Nitoflor EPU2000 epoxy polyurethane coating and Nitoprime 25 primer have a shelf life of 12 months when stored in warehouse conditions below 35°C.

## Precautions

### Health and Safety instructions

Nitoflor EPU2000 epoxy polyurethane coating base and hardener components, colour paste, Nitoprime 25 and Nitoflor Sol should not come in contact with skin and eyes or be swallowed. Prolonged inhalation of solvent vapours should be avoided.

Since some people are sensitive to epoxy resins, hardeners and solvents, gloves, goggles and barrier creams should be used. Adequate ventilation should be avoided and if work is in enclosed areas, suitable breathing apparatus must be used.

If mixed resin comes in contact with skin, it must be removed before it hardens with a resin removing cream, followed by washing with soap and water. Solvent should not be used. Contamination of skin with any of the above component products should be removed immediately with soap and water.

Should accidental eye contamination occur with any of the above products, it should be washed well with plenty of clean water and medical advice sought. If swallowed, immediate medical attention is advised.

## Fire

Nitoflor EPU2000 hardener, Nitoprime 25 and Nitoflor Sol are flammable and should not be exposed to naked flames or other sources of ignition. Smoking is prohibited. Containers should be tightly sealed when not in use. Fire should be extinguished with Carbon dioxide or foam. Vomiting should not be induced.

## Flash points

Nitoflor EPU2000 Hardener	39°C
Nitoprime 25	25°C
Nitoflor Sol	33°C

## Additional information

The Nitoflor range of industrial flooring products for most industrial environments such as abrasion, chemical attack and impact. The product range includes coatings, toppings and sealants to meet the requirements of end users such as workshops, food and drink manufacturing industries, warehouses, hospitals, laboratories, steel, sugar and paper industries, aircrafts, hampers, mechanical engineering industries, tanneries, refineries, etc. For specific requirements, contact Fosroc.

Separate datasheets are available on these products.

® Denotes the trademark of Fosroc International Limited

### Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone	fax	e-mail
+91 80-22240018/120	+91 80-22233474	india@fosroc.com

### Regional Offices



### Fosroc Chemicals (India) Pvt. Ltd.

#### Head Office

111/3, Hafeeza Chamber II Floor,  
K H Road, PBN0. 2744, Bangalore 560027

[www.fosroc.com](http://www.fosroc.com)

#### Bangalore

Shankar House, IV Floor  
1 & 18, RMV Extension  
Bangalore 560 080  
Ph:080-2361 3161/2361 2004  
Fax : 080-2361 7454  
email: Bangalore@fosroc.com

#### Mumbai

208/209, Persepolis  
Sector 17, Vashi  
Navi Mumbai 400 703  
Ph:022-2789 6412/14  
Fax: 022 - 2789 6413  
email:Mumbai@fosroc.com

#### Delhi

First floor,1/2 East Patel Nagar  
Opp: Vivek Cinema, Main Patel Rd  
New Delhi 110 008  
Ph:011-25884903/4  
Fax: 011- 25884422  
email:Delhi@fosroc.com

#### Kolkata

P-569, Lake Terrace Extn.  
First Floor  
Kolkata 700 029  
Ph: 033 24650917 / 55343188  
Fax: 033-24650891  
email:Kolkata@fosroc.com

- Ahmedabad : (079) 26762799 ● Ankleshwar : (02646) 220704/224687 ● Bhubaneshwar : (0674) 2546415 ● Chennai (044) 24899949/24853383
- Chandigarh : (0172) 2639360 ● Cochin : (0484) 2356668 ● Coimbatore : (0422) 2472966 ● Goa : (0832) 2542465 ● Guwahati (0361) 2548793
- Hyderabad : (040) 27662324/27662425 ● Hubli (0836) 09343402597 ● Indore : (0731) 504339/5061477 ● Jaipur : (0141) 2235349
- Jamshedpur: (0657) 2223848 ● Lucknow : (0522) 2239044 ● Nagercoil 09842134873 ● Visakhapatnam : (0891) 2564850 / 2707607

INDIA/2005/0671/A

