



Nitowrap® CFP 25/50

High performance, high strength, corrosion resistant pultruded Carbon fibre plates

Uses

Nitowrap CFP 25/50 system is used for increasing load carrying capacity of structural members particularly where increase in live load / traffic loads is expected. It can also be used to repair when damage to structural member has occurred due to rebar corrosion, earthquake, fire etc. and also in structural members having design defects such as insufficient reinforcement and structural depth.

Advantages

- **Very high strength to thickness or weight ratio** - Appreciable increase in strength and load carrying capacity without significant increase in dead load.
- **Enhanced stiffness, shear and tensile capacities** - Increased load carrying capacity and better resistance to seismic forces and deflection.
- **Chemical resistant** - excellent resistance to acids and alkalis
- **Thin sections** - Can be effectively used in space constrained areas
- **Economical** - Easy to install, time & labour saving

Description

Nitowrap CFP 25/50 is a composite fibre system where Nitowrap CFP 25/50 carbon strip is used in conjunction with an epoxy adhesive, Nitowrap 40. The system can be protected by a UV resistant coat of Nitowrap 512 in case of atmospherically exposed structures.

Properties

Nitowrap CFP 25/50	CFP25	CFP50
Nominal thickness	1.2 mm	1.2mm
Nominal width	25mm	50mm
c/s area	30 mm ²	60mm ²
Young's modulus	>165000 N/mm ²	>165000 N/mm ²
Tensile strength	>2800 N/mm ²	>2800 N/mm ²
Elongation at break	1.7%	1.7%

Nitowrap 40

Compressive strength	40 N/mm ² at 1 day 75 N/mm ² at 7 days
Shear strength	13 N/mm ²
Pot Life	30 min. @ 40°C
Open time	60 min. @ 40°C
Curing time	7 days

Application Instructions

Surface Preparation

Concrete to be treated shall be free from oil residues, demoulding agents, curing compounds, grout holes and protrusions. The concrete surface to be glued with Carbon strip shall be structurally repaired prior to treatment. Corrosion induced damages shall be repaired with e-chem range of repair mortars and Galvashield XP sacrificial anodes shall be installed wherever necessary. Structural damages shall be repaired by using epoxy grouting / appropriate mortars from the Renderoc range

Mixing

The base and hardener of Nitowrap 40, thixotropic adhesive shall be emptied into a suitable container and mixed with low speed, heavy duty drill fitted with a paddle and ensuring the sides are scrapped down. An uniform grey color should be obtained after mixing thoroughly.

Application

Nitowrap CFP 25/50 Carbon strips shall be cut to the recommended sizes before hand due to the impossibility of joint by lapping. Mixed adhesive is applied using a rubber spatula / serrated trowel or other suitable spreader on to the roughened surface of Nitowrap CFP 25/50 carbon strip such that the thickness of the epoxy adhesive is 4mm. The adhesive applied on Nitowrap CFP 25/50 carbon strip is now adhered to the prepared substrate such that excess mixed adhesive squeezes out from both the sides of the plate. The overflowed excess material shall be removed using rubber spatula or by suitable means.

Nitowrap[®] CFP 25/50

Curing

The adhesive will become tack free in approx. 4-6 hours and fully cured in 7 days.

Cleaning

Tools and equipment shall be cleaned with Nitoflor Sol solvent immediately after use. Hands and skin shall be washed with soap, or an industrial hand cleaner.

Estimating

Packaging

Nitowrap CFP 25/50 is supplied as 100m length / roll
Nitowrap 40 is supplied in 6 kg. pack

Coverage

For Nitowrap CFP25 -

Nitowrap 40 - 18-19 RM/pack @ 4mm thickness

For Nitowrap CFP50 -

Nitowrap 40 - 36-38 RM/pack @ 4mm thickness

Storage

Shelf life

Nitowrap CFP 25/50 - Store in dry warehouse conditions
Nitowrap 40 - At least 12 months, if stored below 35°C in unopened containers.

Precautions

Health & Safety instructions

Some people are sensitive to epoxy resin systems and may develop dermatitis on skin contact. Rubber gloves and / or barrier creams, protective clothing, goggles and respirator shall be worn while handling the materials. Sufficient mechanical and / or local exhaust ventilation shall be provided to maintain easy working conditions. If contact with skin or eyes occurs, washing with plenty of water is suggested. Solvent should not be used. If irritation persists, immediate medical advice shall be sought. Smoking is prohibited during application / handling of the product.

Flash point

Nitowrap 40 (base)	-	100°C
Nitowrap 40 (hardener)	-	100°C
Nitoflor Sol (solvent)	-	33°C

Additional information

The Fosroc range of associated products includes admixtures, curing compounds, flooring system, precision grouts, repair mortars, protective coatings, joining sealants, waterproofing systems and e-chem solutions.

Separate datasheets are available on these range of products.

® Denotes the trademark of Fosroc International Limited

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone	fax	e-mail
++91 80-22240018/120	++91 80-22233474	india@fosroc.com

Regional Offices



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

111/3, Hafeeza Chamber II Floor,
K H Road, PBNo. 2744, Bangalore 560027
www.fosroc.com

Bangalore

Shankar House, IV Floor
1 & 18, RMV Extension
Bangalore 560 080
Ph:080-2361 3161/2361 2004
Fax : 080-2361 7454
email: Bangalore@fosroc.com

Mumbai

208/209, Persepolis
Sector 17, Vashi
Navi Mumbai 400 703
Ph:022-2789 6412/14
Fax: 022 - 2789 6413
email:Mumbai@fosroc.com

Delhi

First floor,1/2 East Patel Nagar
Opp: Vivek Cinema, Main Patel Rd
New Delhi 110 008
Ph:011-25884903/4
Fax: 011- 25884422
email:Delhi@fosroc.com

Kolkata

P-569, Lake Terrace Extn.
First Floor
Kolkata 700 029
Ph: 033 24650917 / 55343188
Fax: 033-24650891
email:Kolkata@fosroc.com

- Ahmedabad : (079) 26762799 ● Ankleshwar : (02646) 220704/224687 ● Bhubaneswar : (0674) 2546415 ● Chennai (044) 24899949/24853383
- Chandigarh : (0172) 2639360 ● Cochin : (0484) 2356668 ● Coimbatore : (0422) 2472966 ● Goa : (0832) 2542465 ● Guwahati (0361) 2548793
- Hyderabad : (040) 27662324/27662425 ● Hubli (0836) 09343402597 ● Indore : (0731) 504339/5061477 ● Jaipur : (0141) 2235349
- Jamshedpur : (0657) 2223848 ● Lucknow : (0522) 2239044 ● Nagercoil 09842134873 ● Visakhapatnam : (0891) 2564850 / 2707607