



# Nitocote® EP140(M)

## Epoxy resin based Micaceous Iron Oxide coating for steel and concrete surfaces

### Uses

A chemical and UV light resistant coating for steel tanks, concrete walls, bridges, concrete and metal columns, sluices and ducts.

### Advantages

- Excellent chemical and UV resistance
- Excellent adhesion
- Equally effective on concrete and metal substrates
- Hygienic smooth surface
- Tough, abrasion resistant film

### Description

Nitocote EP140(M) is based on epoxy polyamide resins and MIO specially formulated to provide a durable coating suitable for application to both vertical and horizontal surfaces. It cures to form a smooth film of 80 microns dft , with good resistance to a wide range of chemicals and ultraviolet light.

### Technical Support

Fosroc provides a technical advisory service supported by a team of specialists in the field.

### Properties

	at 20°C	at 35°C
<b>Pot life</b>	3 hrs	1 1/2 hrs
<b>Cure Time</b>	4-7 hrs	2-5 hrs
<b>Time between coats</b>	5-7 hrs	3-5 hrs
<b>Initial Hardness</b>	24 hrs	18 hrs
<b>Full Cure</b>	7 days	5 days

Below 20°C these times will be increased.

### Specification clauses

#### Protective surface coating

The protective coating shall be Nitocote EP140(M), a two part, MIO epoxy polyamide coating capable of providing UV and chemical resistance to exposed surfaces. The cured film shall provide a smooth surface with a dft of 80 microns.

Nitozinc Primer with a DFT of 40 microns shall be applied on steel surfaces prior to the application of Nitocote EP140(M).

### Application instructions

Where relevant, the applications and preparation should conform to the British Standard Code of Practice CP3003:Part 5, 1966. The advice given below is a summary.

### Preparation

Surface to be coated must be structurally sound, dry and free from loose material. All surface contamination must be removed. Grease and oil should be grit blasted or water jetted. Deeper penetration must be removed by mechanical means. Any laitance must be removed from concrete surface by etching with Reebaklens then washed off and dried. New concrete should be allowed to cure for at least 28 days prior to priming. The moisture content in the base concrete should be less than 5% when tested with a hygrometer.

It is essential that Nitocote EP140(M) is applied to sound clean, dry substrates in order to achieve maximum adhesion between the coating and substrate.

### Mixing

Before mixing, the contents of each can should thoroughly stirred to disperse any settlement which may have taken place during storage.

The entire contents of the smaller hardener can should be poured into the base container and the materials thoroughly mixed for at least 3 minutes. Mechanical mixing using a slow speed ( 300 - 500 rpm ) flameproof drill fitted with a mixing paddle is recommended.

### Coating

Apply the mixed Nitocote EP140(M), to the dry, prepared substrate making sure a continuous film is achieved using a standard paintbrush, good quality lamswool roller or spray equipment.

### Cleaning

Tools and equipment should be cleaned with Nitoflor Sol immediately after use.

### Temperature limitations

Minimum application temperature 15°C

At temperatures below 15°C and above 40°C, please contact your local Fosroc office for guidance.

# Nitocote® EP140(M)

## Estimating

### Packaging

<b>Nitocote EP140(M)</b>	4.5 litre pack
<b>Nitozinc Primer</b>	1 and 5 litre packs
<b>Nitoflor Sol</b>	5 and 20 litre cans
<b>Reebaklens</b>	5 and 20 litre cans

### Coverage

<b>Nitocote EP140(M)</b>	10 m <sup>2</sup> / litre/coat @ 100 microns dft.
<b>Nitozinc Primer</b>	8 m <sup>2</sup> / litre

These above figures are for guidance only. Actual coverage depends on the porosity of the substrate, application thickness etc. On steel substrates, primed with Nitozinc Primer, the coverage will be around 5 m<sup>2</sup> per litre for the first coat and around 6 - 7 m<sup>2</sup> for the second coat.

## Storage

### Shelf life

6 months if stored below 35 deg.c in unopened containers.

## Precautions

### Health & Safety

Some people are sensitive to epoxy resin systems and may develop dermatitis on skin contact. Gloves and barrier creams should be used when handling primers and Nitocote EP140(M). If contact with the skin occurs, wash with soap and copious amounts of water. **DO NOT USE SOLVENT.** Direct contact with the eyes will cause irritation and may cause serious damage if left untreated. Any eye contamination should be washed thoroughly with plenty of water and immediate medical treatment sought. The use of goggles when mixing is recommended. Smoking to be avoided.

### Fire

Nitocote EP140(M) and Nitoflor Sol are flammable. Ensure adequate ventilation when using primers and solvents and do not use near a naked flame.

### Flash Point

Nitoflor Sol	33 °C
Nitocote EP140(M)	25 °C

® Denotes the trademark of Fosroc International Limited

### Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone	fax	e-mail
+91 80-22240018/120	+91 80-22233474	india@fosroc.com

### Regional Offices



### Fosroc Chemicals (India) Pvt. Ltd.

#### Head Office

111/3, Hafeeza Chamber II Floor,  
K H Road, PBNo. 2744, Bangalore 560027  
[www.fosroc.com](http://www.fosroc.com)

#### Bangalore

Shankar House, IV Floor  
1 & 18, RMV Extension  
Bangalore 560 080  
Ph:080-2361 3161/2361 2004  
Fax : 080-2361 7454  
email: Bangalore@fosroc.com

#### Mumbai

208/209, Persepolis  
Sector 17, Vashi  
Navi Mumbai 400 703  
Ph:022-2789 6412/14  
Fax: 022 - 2789 6413  
email:Mumbai@fosroc.com

#### Delhi

First floor,1/2 East Patel Nagar  
Opp: Vivek Cinema, Main Patel Rd  
New Delhi 110 008  
Ph:011-25884903/4  
Fax: 011- 25884422  
email:Delhi@fosroc.com

#### Kolkata

P-569, Lake Terrace Extn.  
First Floor  
Kolkata 700 029  
Ph: 033 24650917 / 55343188  
Fax: 033-24650891  
email:Kolkata@fosroc.com

- Ahmedabad : (079) 26762799 ● Ankleshwar : (02646) 220704/224687 ● Bhubaneshwar : (0674) 2546415 ● Chennai (044) 24899949/24853383
- Chandigarh : (0172) 2639360 ● Cochin : (0484) 2356668 ● Coimbatore : (0422) 2472966 ● Goa : (0832) 2542465 ● Guwahati (0361) 2548793
- Hyderabad : (040) 27662324/27662425 ● Hubli (0836) 09343402597 ● Indore : (0731) 504339/5061477 ● Jaipur : (0141) 2235349
- Jamshedpur: (0657) 2223848 ● Lucknow : (0522) 2239044 ● Nagercoil 09842134873 ● Visakhapatnam : (0891) 2564850 / 2707607