



Brushbond

Acrylic polymer modified elastomeric waterproofing membrane coating for concrete and masonry surfaces

Uses

Brushbond provides a seamless, waterproof coating suitable for use in water tanks, reservoirs, swimming pools, roofs and to ensure water tightness.

Brushbond effectively protects against concrete decay providing a long lasting barrier to waterborne corrosive salts and atmospheric gases.

Brushbond is designed to re-face and even out variations in concrete and masonry surfaces.

Brushbond effectively seals concrete masonry walls and bridges the shrinkage cracks which are static.

Brushbond provides a tough and durable coating which cannot be easily damaged or worn away.

Advantages

- Minimum surface preparation needed - Low labour costs.
- Applied directly to the damp concrete and masonry
- Excellent adhesion - Bonds to porous and nonporous surfaces.
- Non-toxic-ideal for potable water tanks
- Waterproof - Excellent for damp-proofing basements
- Breathable-allows transmission of water vapour from interior of building
- Excellent for concrete roof, leaking brick and masonry walls
- Good resistance to Carbon dioxide and Chloride ion diffusion

Description

Brushbond is a two component acrylic polymer modified elastomeric waterproofing membrane which consists of Brushbond powder and Nitobond BB acrylic emulsion. It requires only the addition of water on site and when mixed in the proper proportions, an easily brushable coating is produced. Brushbond can simply be applied by a stiff brush, or trowel to obtain the desired thickness.

Brushbond powder consists of specially selected cements, graded hard-wearing aggregates and additives supplied in powder and Nitobond BB liquid component of blended acrylic copolymers.

The polymer provides Brushbond with exceptional adhesion, toughness and durability.

Technical Support

The company provides a technical advisory service supported by a team of specialists in the field.

Properties

Pot life at 20°C	:	1 hour
at 35°C	:	20 min.
Mixed Density	:	1.90kg/ltr. (brushable consistency)
Tensile strength (ASTM D 638)	:	2 N/mm ² (at 1.5mm thickness)
Colours	:	Grey and white
Application temperature	:	Not less than 10°C
Toxicity	:	Non-toxic
Adhesion to concrete	:	>1N/mm ²

Brushbond provides an elastomeric protective waterproof coating and is shown to resist positive hydrostatic pressure upto 7 meter head. The degree of resistance of Brushbond to water under pressure depends on the coating thickness. Areas subjected to moderate and heavy loads/hydrostatic pressure. minimum 2mm thickness coating is recommended with screed above.

Application Instructions

Preparation

All the surfaces which are to receive Brushbond, must be free from oil, grease, wax, dirt or any other form of foreign matter which might affect adhesion. Spalled and deeply disintergrated concrete should be removed to sound concrete and repaired with Renderoc System.

Mixing

Nitobond BB is poured into a plastic or metal drum. To this, an equal volume of clean fresh water is added, for brush application consistency. Then mixing is started with a slow speed drill (350-450 rpm). The powder component is added gradually to the liquid avoiding lump formation and mixed for 2-4 minutes. Mix and use. More material should not be mixed than can be used within pot life. Retempering with water should not be done. Keep on stirring during application.

Mixing Ratio

Brushbond Components	Indl.pack	Small pack
Powder	23 kg	6 kg
Nitobond BB	4 L	1 L
Water	4 L	1 L

Application

For best results moisten the surface before coating with Brushbond. Apply the mixed material using a short, stiff bristle brush preferably 100 to 150mm width like a paint. Trowel

Brushbond

applications can be undertaken as necessary using the correct mixing ratio to obtain satisfactory consistency.

Brushbond shall be applied in two coats to achieve 1mm thickness. The second coat of Brushbond shall be applied as soon as the first coat has reached touch dry state.

On hot substrates, i.e., over 40°C surface temperature, a primer coat of mixed Brushbond and water with a slurry like consistency should be applied. Prime only areas that can be coated with Brushbond before the primer dries. Material should not be applied at temperatures below 10°C. It is recommended that for general re-surfacing the total thickness of the applied material be 1 to 2 mm.

Areas subjected to moderate and heavy loads/hydrostatic pressure, minimum 2mm thickness coating is recommended with screed above.

Allow the Brushbond to dry before covering with screed. Sprinkle coarse sand on wet surface of final coat for better adhesion of screed.

Average drying time is 4 to 6 hours at normal temperatures.

Subsequent Finishes

Brushbond provides an aesthetically pleasing surface finish texture depending on the method of application, and does not normally require any further surface finishes.

Brushbond is however compatible with most forms of subsequent coatings.

Cleaning

Brushbond should be removed from tools and equipment immediately after use with clean water. Hardened material can be removed mechanically.

Estimating

Packaging

Brushbond powder is supplied as a package of 23kg (Industrial Pack) and 6kg powder. Nitobond BB is supplied in 4 litres and 1 litre jerry can.

Coverage

This depends on the required consistency. The approximate coverage per pack at even consistency (1 mm thickness) is as follows :

Consistency	Brush Application
Coverage in m ² (23kg + 4lit pack)	16 - 18
Coverage in m ² (6kg + 1lit pack)	4 - 4.5

Allowances should be made for any possible wastages when estimating.

Storage

Brushbond has a shelf life of 6 months in unopened packs, if kept in a dry store. In high humidity locations, the shelf life may be reduced to less than 6 months. Prevent Nitobond BB from freezing.

Precautions

Health and Safety instructions

Brushbond is non-toxic but it is alkaline in nature. Gloves and goggles should be worn. Any splashes to the skin or eyes should be washed off with clean water. In the event of prolonged irritation, medical advice should be sought. Should use a dust mask while handling the powder.

Fire

Brushbond components are non-flammable.

® Denotes the trademark of Fosroc International Limited

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone

++91 80-22240018/120

fax

++91 80-22233474

e-mail

india@fosroc.com

Regional Offices



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

111/3, Hafeeza Chamber II Floor,
K H Road, PBN0. 2744, Bangalore 560027
www.fosroc.com

Bangalore

Shankar House, IV Floor
1 & 18, RMV Extension
Bangalore 560 080
Ph:080-2361 3161/2361 2004
Fax : 080-2361 7454
email: Bangalore@fosroc.com

Mumbai

208/209, Persepolis
Sector 17, Vashi
Navi Mumbai 400 703
Ph:022-2789 6412/14
Fax: 022 - 2789 6413
email:Mumbai@fosroc.com

Delhi

First floor,1/2 East Patel Nagar
Opp: Vivek Cinema, Main Patel Rd
New Delhi 110 008
Ph:011-25884903/4
Fax: 011- 25884422
email:Delhi@fosroc.com

Kolkata

30/B Jodhpur Park
Ground Floor
Kolkata 700 068
Ph: 033 2472 5482
Fax: 033-2472 9921
email:Kolkata@fosroc.com

●Ahmedabad : (079) 26762799 ●Ankleshwar : (02646) 220704/224687 ●Bhubaneshwar : (0674) 2521176 ●Chennai (044) 24899949/24853383
●Chandigarh : (0172) 2639360 ●Cochin : (0484) 2356668 ●Coimbatore : (0422) 2472966 ●Goa : (0832) 2542465 ●Guwahati (0361) 2548793
●Hyderabad : (040) 27662324/27662425 ●Hubli (0836) 3402597 ●Indore : (0731) 504339/5061477 ●Jaipur : (0141) 2235349 ●Lucknow : (0522)
22239044 ●Nagercoil (04652) 2224849 ●Mangalore: (0824) 22272234 ●Visakhapatnam : (0891) 2564850

INDIA/2004/707/D

