



Nitobond® EP Std

General purpose epoxy bonding agent

Uses

Bonding old and new cementitious substrates.

Advantages

- Can be applied on concrete & mortar substrate
- Facilitates improvement in mechanical strength
- Good positive adhesion

Description

Nitobond EP Std is a two component epoxy bonding agent supplied in pre-weighed quantities for ready on-site mixing and use.

Technical Support

The company provides a technical advisory source supported by a team of specialists in the field.

Properties

Pot life	Min. 120 minutes @ 35°C
Full hardness	24 hrs.
Full Cure	7 days
Overlay time	Upto 3 hrs.
Compressive Strength BS 6319 Part 2	40 N/mm ²
Tensile Strength BS6319 Part 7	15 N/mm ²
Flexural Strength BS 6319 Part3	25 N/mm ²
Bond strength ASTM C881	11N/mm ²

Below 20° C, above mentioned times will increase.

Application Instructions

Preparation

All surfaces to be treated must be sound, dust-free and clean. All laitence should be removed by wire-brushing or any other suitable means. Surfaces contaminated with oil or grease, shall be cleaned thoroughly to remove such contaminants.

Mixing

The entire contents of the hardener Can should be poured into the resin container and the two materials thoroughly mixed until a uniform colour is obtained. To facilitate application at temperatures below 10° C the separate components should be warmed in hot water to a maximum of 25° C before mixing.

Coating

Mixed Nitobond EP Std should be brush applied to the prepared substrate. The new concrete should be placed within 3 hours at 35° C to the Nitobond EP Std coated substrate, when it is still in a tacky state.

Cleaning

Tools and equipment shall be cleaned thoroughly after use with Nitoflor Sol.

Estimating

Packaging

Available in 1 Litre and 4 Litre.

Coverage

Actual coverage will depend upon the texture and porosity of the substrates being covered. Typically, 1Litre pack will cover about 2.0-2.5 m² and 4 litre pack around 8.0 - 10.0m² .

Storage

12 months shelf life when stored under normal wear house conditions below 35° C in unopened containers.

Precautions

Health & Safety

Contact with skin and eyes should be avoided. Gloves should be used when handling these products. If contact with the resin occurs, skin should be washed immediately with strong detergent. A resin removing cream should be used. Eye contamination must be immediately washed with sufficient quantity of water and medical treatment sought.

Fire

Nitobond EP Std is flammable. No naked flame should be allowed near the site. Do not smoke during use.

Nitobond® EP Std.

Additional Information

Fosroc manufactures a wide range of products specifically designed for the repair and refurbishment of damaged reinforced concrete. This includes hand-placed and spray grade repair mortars and a comprehensive package of protective coatings. In addition, a wide range of complementary products are available. This includes joint sealants, waterproofing membranes, grouts & anchors and specialised flooring materials.

Separate data sheets are available on these products.

® Denotes the trademark of Fosroc International Limited

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

111/3, Hafeeza Chamber II Floor,
K H Road, PBN0. 2744, Bangalore 560027
www.fosroc.com

telephone	fax	e-mail
++91 80-22240018/120	++91 80-22233474	india@fosroc.com

Regional Offices

Bangalore

Shankar House, IV Floor
1 & 18, RMV Extension
Bangalore 560 080
Ph:080-2361 3161/2361 2004
Fax : 080-2361 7454
email: Bangalore@fosroc.com

Mumbai

208/209, Persepolis
Sector 17, Vashi
Navi Mumbai 400 703
Ph:022-2789 6412/14
Fax: 022 - 2789 6413
email:Mumbai@fosroc.com

Delhi

First floor,1/2 East Patel Nagar
Opp: Vivek Cinema, Main Patel Rd
New Delhi 110 008
Ph:011-25884903/4
Fax: 011- 25884422
email:Delhi@fosroc.com

Kolkata

P-569, Lake Terrace Extn.
First Floor
Kolkata 700 029
Ph: 033 24650917 / 55343188
Fax: 033-24650891
email:Kolkata@fosroc.com

- Ahmedabad : (079) 26762799 ● Ankleshwar :(02646) 220704/224687 ● Bhubaneshwar : (0674) 2546415 ● Chennai (044) 24899949/24853383
- Chandigarh : (0172) 2639360 ● Cochin : (0484) 2356668 ● Coimbatore : (0422) 2472966 ● Goa : (0832) 2542465 ● Guwahati (0361) 2548793
- Hyderabad : (040) 27662324/27662425 ● Hubli (0836) 09343402597 ● Indore : (0731) 504339/5061477 ● Jaipur : (0141) 2235349
- Jamshedpur : (0657) 2223848 ● Lucknow :(0522) 2239044 ● Nagercoil 09842134873 ● Visakhapatnam : (0891) 2564850 / 2707607